

AD-749 705

NADC

NAVAL AIR Tech. Info
DEVELOPMENT
CENTER

WARMINSTER, PA. 18974

REPORT NO. NADC-72159-VT

30 AUG 1972

EVALUATION OF CORROSION
INHIBITING PIGMENTS FOR ALUMINUM

PHASE REPORT

AIRTASK WF51543202
Work Unit D

Approved for public release; distribution unlimited.

DTIC QUALITY INSPECTED

NADC-72159-VT

N O T I C E

PRODUCT ENDORSEMENT - The discussion or instructions concerning commercial products herein do not constitute an endorsement by the Government nor do they convey or imply the license or right to use such products.



DEPARTMENT OF THE NAVY
NAVAL AIR DEVELOPMENT CENTER
WARMINSTER, PA. 18974

REPORT NO. NADC-72159-VT

30 AUG 1972

EVALUATION OF CORROSION INHIBITING PIGMENTS FOR ALUMINUM
PHASE REPORT

AIRTASK WF51543202
Work Unit D

Laboratory corrosion tests of inhibitors indicate that the inhibitors which contain hexavalent chromium gave the best protection for aluminum. However, potassium permanganate, also an oxidizing agent which deposits manganese dioxide on the aluminum, prevents corrosion. For screening inhibitors, a weighed aluminum coupon was immersed in a 5% sodium chloride solution containing 0.1% of inhibitor. The coupon was left undisturbed for approximately three weeks. It was then rinsed in distilled water, dried, and weighed and examined visually.

Reported by:

W. C. Marshall
W. C. MARSHALL
Protective Coatings Section

Reviewed by:

A. I. Falkowitz
for A. I. FALKOWITZ
Protective Coatings Section

Approved by:

G. K. Holmes
G. K. HOLMES, Head
Materials Protection Branch

F. S. Williams
F. S. WILLIAMS, Superintendent
Aero Materials Laboratory

Approved for public release; distribution unlimited.

S U M M A R Y

INTRODUCTION

The purpose of this investigation which was performed under AIRTASK number WF51543202, Work Unit D, was to screen various inhibitors for their corrosion protection of aluminum alloys. Some of these inhibitors were evaluated because of their alleged protection of steel. A secondary objective was to find what type of chemicals or pigments afford protection for aluminum.

SUMMARY OF RESULTS

The use of inhibitors having some solubility of hexavalent chromium in the salt solution, as evidenced by the characteristic chromate ion color, resulted in very little weight loss of the aluminum coupon, and very little visible corrosion.

Materials which are insoluble in the salt solution permitted high weight losses and severe visual corrosion.

There was excellent correlation between weight losses of the aluminum coupons and their visible corrosion.

CONCLUSIONS

Pigments or chemicals which contain water soluble chromates afford the best corrosion protection for aluminum alloy. Likewise water soluble compounds such as potassium permanganate, which is also a strong oxidizing agent and deposits insoluble manganese dioxide on the aluminum surface is also satisfactory.

In screening materials for their corrosion protection of aluminum, the weight loss of the coupon plus its visual examination for corrosion is a satisfactory technique for selecting materials which will subsequently be compounded into a paint and further evaluated.

Inhibitive pigments which may be satisfactory for steel are not necessarily good inhibitors for aluminum.

RECOMMENDATIONS

a. Zinc and strontium chromates, combining as they do low cost with adequately controlled water solubility, be the only chromate pigments used for the protection of aluminum alloys.

b. The technique of immersing an aluminum coupon into a 5% salt solution containing the inhibitor, be adopted as a standard screening test because of its good correlation with more sophisticated tests.

TABLE OF CONTENTS

	<u>Page No.</u>
SUMMARY	
Introduction	iii
Summary of Results	iii
Conclusion	iii
Recommendation	iii
EVALUATION AND DISCUSSION	
Background	1
Development of Methods and Results	1
TABLE I	
Corrosion Evaluation of Various Inhibitors	2
LIST OF FIGURES	
1. 7075 Aluminum Alloy Specimens Suspended in 5% Salt Solution Containing 0.10% Inhibitor	3
2. 7075 Aluminum Alloy Specimens Suspended in 5% Salt Solution Containing 0.10% Inhibitor	4
3. 7075 Aluminum Alloy Specimens Suspended in 5% Salt Solution Containing 0.10% Inhibitor	5

EVALUATION AND DISCUSSION

BACKGROUND

The fastener areas, edges of seams, areas where the paint has flaked and other bare aluminum areas on naval aircraft are corrosion prone because they are frequently in contact with salt water as well as sulfur dioxide and particulate matter from smoke stacks. The purpose of this assignment was to screen various inhibitors, some of which are used to protect steel. If the screening test showed other commercially available pigments to be equal or superior to the presently used strontium chromate, then appropriate primers would be made and further evaluated.

DEVELOPMENT OF METHODS AND RESULTS

Coupons, 2 in. X 2 in. X .020 in. were cut from 7075T6 aluminum alloy. The coupons were cleaned with acetone, weighed and suspended with a string in a glass jar containing 5% sodium chloride solution and 0.10% of the inhibitor and capped. The coupons were suspended in the inhibitor/salt solution for 21 days. They were then removed, rinsed in distilled water, dried and weighed. The coupons were examined visually for corrosion.

Table I lists the inhibitors, weight loss and appearance of the coupons after immersion in the salt solution. Figures I to III are photographs of the suspended specimens.

T A B L E I

CORROSION EVALUATION OF VARIOUS INHIBITORS
IMMERSED IN 5% SALT SOLUTION FOR 21 DAYS

<u>INHIBITOR, 0.10% (1,000 PPM)</u>	<u>AVERAGE WEIGHT</u> (Gain or Loss)	<u>APPEARANCE</u>
Strontium Chromate	- 2.0 Mg.	No corrosion
Strontium Molybdate	- 33.1 Mg.	Severe corrosion
Zinc Molybdate	- 4.7 Mg.	Moderate corrosion
Zinc Phosphate	- 17.9 Mg.	Severe corrosion
Aluminum Phosphate	- 37.1 Mg.	Severe corrosion
Potassium Chromate	- 1.3 Mg.	No corrosion
Potassium Permanganate	- 3.9 Mg.	Slight corrosion
Chromium Chromate	+ 2.5 Mg.	Slight corrosion
Cadmium Phosphate Chromate	+ 4.5 Mg.	Slight corrosion



Figure 1. - 7075-Aluminum Alloy Specimen Suspended in 5% Salt Solution Containing 0.1% Inhibitor



Figure 2. - 7075-Aluminum Alloy Specimen Suspended in
5% Salt Solution Containing 0.1% Inhibitor



Figure 3. - 7075-Aluminum Alloy Specimen Suspended in
5% Salt Solution Containing 0.1% Inhibitor

DOCUMENT CONTROL DATA - R & D

Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY (Corporate author)

Naval Air Development Center
Air Vehicle Technology Department
Warminster, Pennsylvania 18974

2a. REPORT SECURITY CLASSIFICATION

UNCLASSIFIED

2b. GROUP

3. REPORT TITLE

EVALUATION OF CORROSION INHIBITING PIGMENTS FOR ALUMINUM

4. DESCRIPTIVE NOTES (Type of report and inclusive dates)

PHASE

5. AUTHOR(S) (First name, middle initial, last name)

WILLIAM C. MARSHALL

6. REPORT DATE

30 AUGUST 1972

7a. TOTAL NO. OF PAGES

9

7b. NO. OF REFS

0

8a. CONTRACT OR GRANT NO.

AIRTASK WF51543202

b. PROJECT NO. Work Unit D

9a. ORIGINATOR'S REPORT NUMBER(S)

NADC-72159-VT

9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)

10. DISTRIBUTION STATEMENT

Approved for public release; distribution unlimited.

11. SUPPLEMENTARY NOTES

12. SPONSORING MILITARY ACTIVITY

Naval Air Systems Command
Washington, D.C. 20360

13. ABSTRACT

Laboratory corrosion tests of inhibitors indicate that the inhibitors which contain hexavalent chromium gave the best protection for aluminum. However, potassium permanganate, also an oxidizing agent which deposits manganese dioxide on the aluminum, prevents corrosion. For screening inhibitors, a weighed aluminum coupon was immersed in a 5% sodium chloride solution containing 0.1% of inhibitor. The coupon was left undisturbed for approximately three weeks. It was then rinsed in distilled water, dried, and weighed and examined visually.

14

KEY WORDS

LINK A

LINK B

LINK C

ROLE

WT

ROLE

WT

ROLE

WT

Corrosion
Inhibitor
Hexavalent Chromium
Corrosion Protection
Aluminum Alloy

D I S T R I B U T I O N L I S T

REPORT NO. NADC-72159-VT

AIRTASK WF51543202

Work Unit D

	<u>No. of Copies</u>
NAVAIR (AIR 604)	6
(2 for retention)	
(1 for AIR 5203)	
(1 for AIR 52033)	
(1 for AIR 4117B)	
(1 for AIR 320A)	
NAVAIRSYSCOMREPLANT	1
NAVAIRSYSCOMREPAC	1
COMNAVAIRLANT	1
COMNAVAIRPAC	1
WPAFB, Ohio (R&T Div., MAAS)	1
NAFI, Indiana	1
NARF, NAS Alameda	1
NARF, NAS Jacksonville	1
NARF, NAS Norfolk	1
NARF, NAS North Island	1
NARF, NAS Pensacola	1
NARF, NAS Quonset Point	1
MCAS, Cherry Point	1
NAPTC (AED)	1
ABERDEEN PROVING GROUND, Aberdeen, Md.	1
NAVAIRDEVCECEN.	24
(3 for ADT)	(10 for VTMP)
(1 for AE)	(1 for VTR)
(1 for ASW)	(1 for VTS)
(1 for CS)	
(1 for SD)	
(1 for SDS)	
(1 for SDX)	
(3 for VTA)	